

	VITAL TECHNICAL SDN. BHD.	  	Issued date : 31/03/08
	Technical Data Sheet		Rev. No. : 4
	VT-131 Auto Sealer		Revised date : 30/04/13
			Page : 1 of 1

Product Specifications:

Physical Properties

Curing system:	Oxime
Appearance:	Paste
Color:	Black
Odor:	Slight unique odor
Specific Gravity:	1.04
Tack-Free Time JIS A 1439:	≤30 min
Application Temperature:	-20 °C to 50 °C
Service Temperature:	-50 to 150 °C
Shelf life:	12 months
Tensile at break:	≥0.8 MPa
Elongation at break:	≥250%



Product Description:

A one component, general purpose, black silicone sealant for both indoor and outdoor applications. It may be applied to horizontal or vertical surfaces. It provides a waterproof and flexible seals and resists oil, water, weather, vibration and grease. It does not dry out or become brittle.

Applications:

It seals, bonds, repairs, mends and secures glass, metal, plastics, fabric, vinyl, weather-stripping and vinyl tops. It can also be used to protect and repair electrical wiring, windshields, door frames, electrical connections, seams and roofs.

Directions:

1. Surfaces must be clean, dry and free of dirt, grease, oil or water. Puncture the tube with the cap and install nozzle.
2. Squeeze tube and push sealant ahead of nozzle to achieve a smooth finish. Sealant skins in 5 minutes, dries to touch in 1 hour and is fully cured in 24 hours.
3. Uncured sealant can be cleaned up with mineral spirits.
4. Replace cap after use and store in a cool, dry place.

Caution:

Uncured sealant causes skin and eyes irritation upon contact. Avoid prolonged contact with eyes or skin. In case of eyes contact, flush with water for 15 minutes and seek medical attention immediately. In case of skin contact, wipe off and wash with soap and water.

Keep out of reach of children. Use in well ventilated areas.

Storage:

- Store in a dry and cool place with temperature below +30°C.
- Use within 12 months from date of production.

Every endeavour has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The company will not accept any responsibility for the loss or damage that may result from the use of the information, due to the possibility of various of processing or working conditions and of workmanship outside our control. Users are advised to confirm suitability of this product by their own tests.

- END -